



suppliers of passive fire products, acoustic and specialist insulation
manufacturers of the Safire Fire Stopping Range

Safire Batts - Acoustic Performance Test Data

These test have been done in line with the British Standard Test Method as laid ou in document E sound reduction levels;

1 x 40mm Safire Coated Batt	31 db
2 x 40mm Safire Caoted Batt	49 db
1 x 50mm Safire Coated Batt	33 db
2 x 50mm Safire Coated Batt	50 db
1 x 60mm Safire Coated Batt	35 db
2 x 60mm Safire Coated Batt	52 db

Please note that these results are room to room reductions for typical seal using the the standard installation details

It must be noted that these figures have been gained using test conditions other factors on other constructions may effect the overall sound performance

Fire-Us Ltd.

Unit 6 Thetis Road, Lune Industrial Estate, Lancaster, LA1 5QP

Tel. 01524 388898 Fax. 01524 383724 Email. info@fireus.co.uk Web. www.fireus.co.uk